



Home Innovation
RESEARCH LABS

**Report of Tests Results
In Accordance With
ASTM F462 Slip Resistance**

Prepared For:

Sander & Sons Kitchen and Bath
7540 S. Grant Street
Littleton, CO 80122

Prepared By:
Home Innovation Research Labs

Report # 4161-005-6548-1216

Date of Issue:
December 29, 2016

TABLE OF CONTENTS

I.	Purpose	1
II.	Background	1
III.	Test Methodology	1
IV.	Test Results	3
V.	Discussion of Results	3

I. PURPOSE

The finished surfaces of bathing fixtures may be exceedingly slippery when wet. Therefore, many manufacturers have devised textured surfaces in order to prevent slipping. The purpose of this test is to measure the static coefficient of friction (resistance to slipping) of a given "slip resistant" surface to determine if it meets a minimum performance requirement.

The standard procedure for evaluating the slip resistance of slip resistant bath fixture is defined in the ASTM F462 Standard Consumer Safety Specification for Slip Resistant Bathing Facilities. The slip resistance test involves the use of a device known as a Brungraber Slip Resistance Tester. Measurements are taken in nine different "measurement zones" (different locations on the slip resistant surface) with the Brungraber tester. Two measurements are taken in each measurement zone, and the resulting data is used to calculate μ_s values. The two values μ_s obtained from each measurement zone are averaged, resulting in nine μ_s values for the entire surface.

After completion of the calculations, the resulting coefficients are compared to the performance requirement of the ASTM F462 standard. Conformance to the standard requires that each of the nine tested locations yield an average μ_s value of no less than 0.04.

II. BACKGROUND

Sander & Sons Kitchen and Bath contacted Home Innovation Research Labs to request testing in accordance with the ASTM F462 standard.

One solid surface panel was submitted for evaluation. The material was received on November 16, 2016 and marked as "100 Grit". The testing was conducted on December 08, 2016.

III. TEST METHODOLOGY

ASTM F462

Test Preparation:

Prior to testing, the surface of the unit is thoroughly cleaned with a non-abrasive compound. The sample is then leveled and the drain is sealed. The unit is subsequently filled with a soap solution, as described in Section 8.3 of the ASTM F462 standard, to a minimum depth of 1/2".

Test Method:

Nine different locations on the slip resistant surface are tested. These locations are defined as "measurement zones" in the ASTM F462 standard. The Brungraber Slip Resistance Tester is then applied to the surface. Two measurements are taken in each measurement zone.

The Brungraber Slip Resistance Tester is designed to measure the static coefficient of friction between a representative foot surface and a surface for walking or standing. This is accomplished when the operator applies a predetermined vertical force through vertical shafts and an articulated shaft to the sensor shoe.

At the start of the test, the carriage is brought forward to a stop position such that the articulated shaft is not vertical but set at a slight angle towards the back of the tester. This is accomplished by either introducing an initial position stop at the front of the carriage or by using the tester in an "uphill" mode on a surface inclined to an angle of at least 1 degree. This establishes an unbalanced lateral force against the carriage. At the instant that the handle is released and the vertical load is applied, the carriage begins to move back along the travel bars, inducing an increasing lateral load on the shoe as the angle between the articulated shaft and the vertical shaft increases. The tangent of this angle at the instant that slip occurs is directly related to the static coefficient of friction. This angle is measured by the recording shaft, which is magnetized and drawn along by the attachment of the attraction plate as the carriage moves backwards. When slip occurs, the sensor shoe hits the trigger so that the recorder clamp grips the recording shaft, retaining the shaft in the position assumed at the time of slip. The measurement of slip resistance is read opposite a notch in the indicator tube at the front of the recorder clamp from a linear-graduated scale imprinted along the length of the recorder shaft. This value is directly translated to the static coefficient of friction by use of the calibration chart or table supplied with the tester.

After all measurements have been completed, the two measurements for each measurement zone are averaged. These average static coefficients of friction are the reported values for each measurement zone.

Performance Requirement:

Section 9.2 of the ASTM F462 standard states that the average static coefficient of friction for all measurement zones shall be **no less than 0.04**.

IV. TEST RESULTS – ASTM F462

Sample Corian 100 Grit Slip Test Results

Measurement Zone	Average Static Coefficient of Friction	Test Result
1	0.175	Pass
2	0.139	Pass
3	0.173	Pass
4	0.183	Pass
5	0.188	Pass
6	0.181	Pass
7	0.190	Pass
8	0.176	Pass
9	0.185	Pass
Average	0.177	Pass

V. DISCUSSION OF RESULTS

The samples were not damaged during shipping and they did not appear that they were tampered with prior to arrival. These tests were performed under the direct and continuous supervision of laboratory personnel. The plastic panels, as received, **passed** the ASTM F462 standard as detailed in this report.



Sam Yuan, Ph.D., P.E.
Director of Laboratory and Certifications

This report may be distributed in its entirety but excerpted portions shall not be distributed without prior written approval of Home Innovation Research Labs.